

ACCUFAM 2.8 SPRAY POLYURETHANE FOAM ROOFING INSULATION

PRODUCT DESCRIPTION

ACCUFAM 2.8 is an HFC-blown, Zero Ozone-Depleting (Zero-ODP), spray polyurethane foam (SPF) system designed for roofing applications. ACCUFAM 2.8 is compatible with most common construction materials.

TYPICAL PROPERTIES ⁽¹⁾

PROPERTY	METHOD	VALUE
RESIN:		
Specific Gravity @ 70°F	ASTM D 1638	1.18
Viscosity @ 70°F (cps)	Brookfield	900 – 1200
CURED FOAM:		
Mix Ratio (volume:volume)		1:1
Density(pcf)	ASTM D 1622	2.8 – 2.9
Thermal Resistance		
R-value (ft ² hr °F/Btu in)		6.3/in
Compressive Strength (psi)	ASTM D 1621	50 +/- 5%
Tensile Strength (psi)	ASTM D 1623	60 – 80
Shear Strength (psi)	ASTM C 273	40 – 60
Closed Cell Content (%)	ASTM D 6226	>95
Water Vapor Transmission		
Permeability (perm-inch)	ASTM E 96	<2.5
Dimensional Stability	ASTM D 2126	<4%
SURFACE BURNING CHARACTERISTICS		
Flame Spread Index(3)	ASTM E 84	<25

ADDITIONAL TESTING, APPROVALS & CERTIFICATIONS:

- ASTM C 1029
- ASTM E 108

NON-COMBUSTIBLE DECKS

- > Class A up to Unlimited thickness of SPF
- > Silicone, Acrylic and Urethane coating options
- > Granules at 35 lbs per 100 ft² depending on configuration

COMBUSTIBLE DECKS

- > Class B at 1 inch (min) SPF thickness
- > Silicone, Acrylic and Urethane coating options
- > Granules at 35 lbs per 100 ft² depending on configuration
- Florida Building Code Approval FL 1493.1^(*)
- Miami-Dade County Approvals^(*)
- Texas Department of Insurance (TDI) Product Evaluation RC-291^(*)


^(*)approvals pending

GENERAL INFORMATION:

ACCUF³AM 2.8 is a spray polyurethane foam (SPF) system intended for installation by qualified contractors trained in the processing and application of SPF systems, as well as the plural-component polyurethane dispensing equipment required to do so. Contractors and applicators must comply with all applicable and appropriate storage, handling, processing and safety guidelines. ACCUF³AM technical service personnel should be consulted in all cases where application conditions are questionable.

ACCUF³AM 2.8 is available in several reactivity. Some suggested ambient temperature ranges for each of the reactivity grades is included below:

SUGGESTED AMBIENT TEMPERATURE RANGES



CAUTIONS AND RECOMMENDATIONS:

ACCUF³AM 2.8 is designed for an application rate of ½ inch minimum to 1½ inches maximum per pass. Once installed and material has cooled it is possible to add additional applications in order to increase the overall installed thickness of SPF. Thicker installations are allowed based on large scale testing. This application procedure is in compliance with the Spray Polyurethane Foam Alliance (SPFA).

ACCUF³AM 2.8 is NOT designed for use as an INTERIOR insulation system. ACCUF³AM offers a separate line of products for interior insulation applications. For more information, please contact your sales representative.

ACCUF³AM 2.8 is designed for installation to most standard construction materials such as wood, wood-based products, plastics, metal and concrete. Applications can be done at approximately 50°F and warming using special cold weather application techniques. Please consult a ACCUF³AM Representative for further information about applications using our liquid compounds. In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems. Personnel should review the following documents published by Spray Polyurethane Foam Alliance (SPFA):

AX-171 Course 101-R Chapter 1: Health, Safety and Environmental Aspects of Spray Polyurethane Foam and Coverings www.spraypolyurethane.org and the following document is available from the Center for the Polyurethanes Industries (CPI):

Model Respiratory Protection Program for Compliance with the Occupational Safety and Health Administration's Respiratory Protection Program Standard 29 C.F.R. §1910.134

As with all SPF systems, improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. **Potential results of improperly installed SPF include: dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed materials.**

LARGE MASSES of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into any trash receptacle.

SPF insulation is combustible. High-intensity heat sources such as welding or cutting torches must not be used in contact with or in close proximity to ACCUF³AM 2.8 or any polyurethane foam.

SHELF LIFE AND STORAGE CONDITIONS:

ACCUF³AM 2.8 has a shelf life of approximately (6) months from the date of manufacture when stored in original, unopened containers at 50- 80°F. As with all industrial chemicals this material should be stored in a covered, secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life. Storage temperatures above the recommended range may also result in elevated headspace pressure within packages.

DISCLAIMER: The data herein is to assist customers who desire to use our products to determine if the products are safe and suitable for their applications. The data presented herein is not intended for use by non-professional applicators, or those persons who do not purchase or utilize this product in the normal course of their business. Customers further assume full responsibility for quality control, testing and determining whether the products are suitable for each individual application. To the best of Creative Polymers knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE SUED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF CREATIVE POLYMER'S TERMS AND CONDITIONS OF SALE.**